

Insert pages for September 1, 2011 Wisconsin Commercial Building Code, Comm 61-66, into the International Building Code, 2009 edition

Safety and Buildings Division - Wisconsin Department of Safety and Professional Services

IBC Chapter 21, Insert 21A, Page 1 of 1
 Insert between pages 436 and 437

Comm 62.2109 Empirical design of masonry. (1) BEARING ON MASONRY. This is a department rule in addition to the requirements in IBC section 2109.1: Lintels shall be considered structural members and shall be designed in accordance with the applicable provisions of IBC chapter 16.

(2) JOINTING. These are department rules in addition to the requirements in IBC section 2109:
 (a) *Expansion and shrinkage.* Joints commensurate with lateral stability requirements shall be installed in all exterior masonry to allow for expected growth of clay products and shrinkage of concrete products.

(b) *Vertical jointing.* Vertical movement joints shall be provided at a spacing in compliance with Table 62.2109.

Note: To accomplish the intended purpose, joints should be located at critical locations, such as changes in building heights, changes in framing systems, columns built into exterior walls, major wall openings, and changes in materials.

(c) *Horizontal jointing.* Where supports such as shelf angles or plates are required to carry the weight of masonry above the foundation level, a pressure-relieving joint shall be provided between the structural support and any masonry that occurs below this level. The joint width shall be such as to prevent any load being transmitted from the support to any element directly below. All mortar and rigid materials shall be kept out of this joint. This type of joint shall be provided at all such supports in a concrete frame structure where clay masonry is exposed to the weather.

**Table 62.2109
 Maximum Spacing Of Exterior Masonry Movement Joints
 Between Unrestrained Ends† (Feet)**

Loading Conditions	Type of Material	Openings (Percent of Total Wall Area)			
		0 to 20		More than 20	
		Joint to Joint	Joint to Corner	Joint to Joint	Joint to Corner
Load-bearing	Clay units	140	70	100	50
	Concrete units	60	30	40	20
Nonload-bearing walls	Clay units	100	50	60	40
	Concrete units	50	25	30	20

†Jointing required is a minimum and is not intended to prevent minor cracking. The distances given for maximum spacing of joints are for a single wall plane. For composite walls, the maximum spacing of joints shall be governed by the masonry material type used in the exterior wythe.